


AQUApro Select CT 8.0 Sm P

Product description

P i05

Stand: 10.21



Tests		Flooring ¹ Symbols	Results
Panel dimension			1290x329x8mm
Service category per Standard per	EN ISO 10874 EN 13329		33
Abrasion resistance	EN 13329		AC5
Impact resistance small ball big ball	EN 13329		≥15N ≥1000mm
Formaldehyde emission of the substrate before coating	EN 120 DIBT- Richtlinie 100		E1 [Europe]
Formaldehyde emission	EN 717-1		< 0,1 ppm
	EN 717-2		< 3,5 mg/h m²

All values are approximate values - fluctuations cannot be absolutely ruled out.

Formaldehyde emission/ VOC			GREENGUARD GOLD
Formaldehyde emission	CARB		CARB Phase 2
Edge swelling	EN 13329		≤ 12%
Thermal conductivity	ISO 8302		0,0780 m² K/W
Moisture residue HDF	EN 322		4 - 7 %
Resistance to cigarette burns	EN 438-2.18		grade 4
Light fastness	EN ISO 105-B02 EN 20105-A02		not worse than 6 Blue wool scale not worse than 4 Grey scale
Lifting resistance	EN 13329		≥ 1,25N/mm²
Resistance to stains	EN 438-2.15		groups 1-2 grade 5 group 3 grade 4
Combustibility	EN13501-1		Cfl , s1
Water resistance	NALFA surface watertest 01.08.2019		qualitativ ≤ 2 and ≤0,3mm
Sliding friction μ	EN 13893		≥ 0,3
Dimensional variants after changes in relative humidity	EN 13329		length and width ≤ 0,9 mm
Straightness of the panels	EN 13329		≤ 0,30 mm /m
Height difference between elements	EN 13329		maximum ≤ 0,15 mm average ≤ 0,10 mm
Squared elements	EN 13329		≤ 0,2 mm / panel width
Flatness of the element width	EN 13329		concave <= 0,5 mm convex <= 0,7 mm concave <= 6 mm
Flatness of the element length	EN 13329		convex <= 13 mm
System pattern matching widthwise			+/- 2mm
Ship's planking matching widthwise			+/- 4mm

¹⁾Information under www.floorsymbols.com